


ASTM D4060 TESTING
ON SUPERTHERM
FOR
SUPERIOR PRODUCTS
VTEC 100-716-4
TESTED: JULY 21, 1997



VTEC LABORATORIES INC.

212 Manida Street
Bronx, New York 10474
(718) 542-8248
FAX: (718) 542-8759



VTEC Laboratories Inc.

July 21, 1997

I. Introduction:

1) Client: Superior Products
6459 Universal Ave.
Kansas City, MO 64120

2) Attention: Mr. J.E. Pritchett

3) Scope: This report contains the reference to the test method, preparation and conditioning of sample, observation of material, test and post test observation data test results.

4) Test Method: This test was conducted in accordance with ASTM D4060 specification.

4.1 This standard should be used to determine the resistance of organic coatings to abrasion produced by the Taber Abraser on coatings applied to a plane, rigid surface, such as a metal panel.

DISCLAIMER:

This is a factual report of the results obtained from the laboratory test of sample products. The results may be applied only to the products tested and should not be construed as applicable to other similar products of the manufacturer. The report is not a recommendation or a disapprobation by VTEC Laboratories, Inc. of the material tested. While this report may be used for obtaining product acceptance, it may not be used in advertising.

Notice: VTEC Laboratories Inc. will not be liable for any loss or damage resulting from the use of the data in this report, in excess of the invoice. This report pertains to the sample tested only. Such report shall not be interpreted to be a warranty, either expressed or implied as to the suitability or fitness of said sample for such uses or applications, as the party contracting for the report may apply such sample.

Test No. VTEC 100-716-4

Date of Test: July 21, 1997


II Material Tested:


- 1) Manufacturer: Superior Products
- 2) Product Description: Supertherm
- 3) Color: White
- 4) Number of Specimens: 2
- 5) Surface: Smooth
- 6) Material description: by Manufacturer and VTEC
- 7) Date of selection: April 3, 1997
- 8) Purpose of test: Abrasion Resistance of Organic Coatings by the Taber Abraser.
- 9) Method of sample mounting: Painted on Metal Disks

Good

III Test Results

# of Cycles	3,000 cycles
Wheel Size	CS 17
Load On Wheels	1,000 grams
	<u>Wear Index</u>
Sample 1	657
Sample 2	568


Neil Schultz
Executive Director


Amirudin Rahim
Technical Director